

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (currently amended): A crosslinkable elastomer composition for plasma process comprising a crosslinkable elastomer and a carbon fluoride filler,
wherein said carbon fluoride filler is heat treated at 300 to 550°C in advance.
2. (original): The crosslinkable elastomer composition of Claim 1, which further comprises a silicic compound inorganic filler and/or a filler comprising a synthetic polymer having a thermally and chemically stable aromatic ring in the main chain.
3. (original): The crosslinkable elastomer composition of Claim 2, wherein said synthetic polymer having a thermally and chemically stable aromatic ring in the main chain is a synthetic polymer having an amide bond or an imide bond in the main chain.
4. (original): The crosslinkable elastomer composition of Claim 2, wherein said silicic compound inorganic filler has average particle size of at most 0.5 μm .
5. (original): The crosslinkable elastomer composition of Claim 2, wherein said filler comprising a synthetic polymer having a thermally and chemically stable aromatic ring in the main chain has specific surface area of at least 0.5 m^2/g .
6. (canceled).
7. (previously presented): The crosslinkable elastomer composition of Claim 1, wherein said crosslinkable elastomer is a perfluoro elastomer.

8. (previously presented): A molded article for plasma process comprising the crosslinkable elastomer composition of Claim 1.

9. (previously presented): A sealing material for plasma process comprising the crosslinkable elastomer composition of Claim 1.